



# Vented Single Cell Ni-Cd Battery Range





## 140 YEARS OF EXCELLENCE

Throughout our rich history, Geräte- und Akkumulatorenwerk Zwickau has always been at the forefront of technological development. Today we rank among the leading suppliers of industrial Ni-Cd batteries and energy storage solutions based on Li-ion batteries.

We develop and manufacture Ni-Cd cells of highest quality, pushing the boundaries of this proven chemistry with innovative design features. Delivering customized battery solutions to customers around the world, our battery systems serve as backup power sources for critical equipment in industries ranging from oil and gas, energy and communications to transportation and other infrastructure.

## APPLICATIONS

GAZ® Ni-Cd batteries are built to withstand mechanical and electrical stress as well as extreme temperatures. Their ruggedness makes them ideal for deployment in challenging conditions such as oil and gas, excavation, transmission and refineries, utility power generation and Transmission and distribution, substations, telecom installations, or transportation infrastructure.

With their design lifespan exceeding 20 years and minimal maintenance requirements, GAZ® Ni-Cd batteries offer unparalleled reliability whenever the risk of failure is unacceptable. They provide backup power for all kinds of critical installations even in the most extreme conditions and remote locations. Industrial facilities, large data centers, commercial buildings, hospitals, airport infrastructure, all rely on GAZ® Ni-Cd batteries.

Their durability and high discharge rate performance makes GAZ® Ni-Cd batteries particularly suitable for inrush

applications such as cranking generators or switching on heaters, circulation pumps, and similar unpredictable, time-sensitive, high-power demanding critical applications that should perform even at extreme temperatures. GAZ batteries recover their voltage instantaneously unlike 'Coup de Fouét' phenomenon for other electro-chemistry, making them the ideal choice for such inrush applications.

- + O&G on-shore, off-shore exploration and refineries
- + Power Generation-Transmission-Distribution,
- + Utility Substations, Switch-Gear and Control-Gear operations
- + Emergency lighting
- + Communication systems – SCADA
- + DC UPS systems
- + Critical processes input power regulation
- + Track-side applications, railway signaling
- + Security-Alarm systems
- + Gen-set / Engine-starting power



## EUROPEAN QUALITY WITHOUT COMPROMISE

GAZ Vented Range cells are built with uncompromised quality and workmanship in accordance to IEC 60623 standards and EU battery regulations. And not only to meet but exceed the performance requirements specified in the standard. Optimized anodic to cathodic capacity ratio and stack-cell designs specific to low, medium and high rate discharge applications guarantees the right price-performance ration without capacity oversizing and compromising on the energy or power or mixed-load performances. Special easy-to-fit and refill vent plugs consists of inert granules that help condensing of escaping gas and reduce water consumption. Vent plugs are fitted with flame arresting disk that prevents external sparks and any explosion.



## SINGLE CELL CONSTRUCTION

### Gas condensation type Flame arresting vent plug

### Safety terminal

Redundant leak protection minimizes carbonate formation

### GAZ single cell design

Weld above the electrolyte level eliminates risk of faulty on the side and on the bottom of the cell

### Electrode edge

Connected to terminals by bolting or welding

### Electrode frame

Consisting of electrode edge and side bars. Seals the plates and works as a current collector

### Solid PP Grid type or Corrugated-Perforated Plastic Separators

Insulates the plates and allows free circulation of electrolyte

### Horizontal pockets

Formed by perforated steel strips containing the active material

### Cell Case and Lid

Unique single cell case mold with only top lid welding eliminate chance of any electrolyte leakage



# INDUSTRIAL NI-CD VENTED BATTERY RANGES

## KL... P / KM... P / KH... P

The robust and well-proven design of GAZ® Ni-Cd cells and batteries offers exceptional reliability for maximum service life and highly favorable Total Cost of Ownership.

Backed by 140 years of tradition in excellence, GAZ® prides itself on the highest possible manufacturing quality. GAZ® Ni-Cd battery cells fulfill all requirements according to IEC 60623 and EN 60623.

### Configuration forms

GAZ® Ni-Cd prismatic cells can be assembled into many different configurations, for example:

- ✓ In battery racks and cabinets
- ✓ Mounted as compact blocks
- ✓ In plastic, FRP, or stainless steel crates, or in battery troughs

### Advantages of Pocket-Plate technology

- + Robust all steel electrode construction. Insensitive against seismic vibration categories, minor mishandling during transit.
- + Proven technology for over 100 years with exceptional reliability in uncertain back-up needs.

- + Excellent high rate power discharge Performance. Can be sized for as low as 1 second discharge.
- + Reliable stationary cycling capability of 20+ years
- + Large electrolyte reserve reduce top-up frequency and periodic maintenance costs in remote sites
- + Lower internal resistance, Higher charge acceptance
- + No risk of 'Sudden-death' or Thermal runaway
- + No electrode corrosion or passivation in cells
- + Better extreme temperature performances. Can also Operate reliably between -40 °C to +70 °C with special GAZ® electrolyte
- + Tolerate faulty over-charge, over-discharge without any loss of capacity but just increased electrolysis
- + Long shelf life of several years in discharged state under GAZ® recommended conditions below +30 °C
- + No electrolyte stratification required. Electrolyte density remain mostly unaltered throughout service life
- + Exceptional Total Cost-of-Ownership (TCO)
- + Better retained capacity at sub-zero temperatures
- + Visible electrolyte level through translucent container
- + No memory effect unlike sealed cylindrical cells

## EFFICIENT DESIGN AND SOLUTION FOR EVERY NEED

GAZ® developed the KL, KM and KH ranges of Ni-Cd vented batteries to offer a both economically and technically flexible solution for every stationary application. The choice of Low, Medium and High rate discharge type makes it easy to select the ideal battery, based on the required discharge time and end of discharge voltage.

	KL...P Range	KM...P Range	KH...P Range
<b>Capacity Steps</b>	94	46	30
<b>Capacity Range</b>	10–1800 Ah	11–1390 Ah	10–800 Ah
<b>Design and Performance</b>	Thickest Plate Design for Low discharge rate > 3 hour	Optimum Plate thickness for Medium or mixed discharge rate.	Thinnest Plate design for High Discharge rate < 45 Min
<b>Maintenance</b>	D/DM water top-up requirement 18–24 months. Preventive maintenance as per IEEE guidelines.		
<b>Typical Market Segment</b>	Utilities, O&G Offshore and Onshore Rigs, Refineries, Commercial & Industrial Buildings, Hospitals, Rail-Infra	Substations, Rapid Transport and O&G Infra, Chemical, Mining and Process Industries, Utility T&D Substations	Utility Generation, Industries, O&G, Commercial & Industrial Buildings, Hospitals, Rail and public Infrastructures
<b>Typical Applications</b>	Auxiliary Energy back-up in Alarm, Signalling Systems, Emergency Lighting, Communication, SCADA	Mix of Energy and Power Back-up applications for UPS Systems, Switchgear, Controlgear	High Power back-up for Genset, Engine Starting, UPS Systems, Substations, Process machineries

## GAZ VENTED KL BATTERY RANGE

This GAZ® cell type has been especially designed for low rates of discharge over long periods, i.e. the current is relatively low in comparison with the total stored energy. The discharges can generally be infrequent and the recommended discharge time for the KL range is above 3 hours.

The nominal  $C_5$  capacity (as per IEC 60623) of KL range batteries is based on the available ampere hours (Ah) at a discharge rate of 5 hours to a final discharge voltage of 1.00 V per cell at  $20 \pm 5$  °C.

### Nominal voltage per cell

1.20 V per cell

### Discharging conditions

The discharge performances as well as the nominal capacities  $C_5$  given in this brochure are only valid for fully charged cells in accordance with IEC 60623 und EN 60623, clause number 7.3.2.

### Charging Recommendation – KL Range

#### A. Constant Voltage (FCBC Chargers)

Recommendation for Stand-by Application

#### Boost Mode

Boost Voltage: 1.55–1.70 V/cell

Boost Current Limit: 0.2 It A dc

**NOTE:** Higher Boost voltage will reduce the charge duration and increase efficiency of recharging but may increase electrolysis and water consumption.

#### Float Mode

Float Voltage: 1.40–1.42 V/cell

Float Current: 1 to 2 mA/Ah cell capacity

Delay for switch from Boost to Float:

Boost Current ramped < 0.004 It A

#### Single level Charging

1.47–1.50 V/cell

### B. Constant Current mode

#### Charging for IEC Capacity Test

Constant Current: 0.2 It A dc for 8 h

Alternatively, 0.1 It A dc CC for 16 h


Voltage Limit: No Voltage Limit

Charging Temperature:  $20 \pm 5$  °C

#### Fast Charging at 25 °C

Boost charge: 0.3 It A for 2.5 h followed by 0.2 It A for 2.5 h

Trickle charge: 0.001–0.002 A/Ah



## KL... P Single Cell Range

### Technical Specifications

"KL Type Models"	IEC-60623 Capacity	"Cell Dimensions [Tolerance ±2 mm]"				Connection Type	Nr. Of Terminals	Type of Terminals	Electrolyte Volume	Filled Cell Weight	Internal Resistance
		l	w	h	h1						
In Plastic Containers	5h rate [C <sub>5</sub> ] [Ah]	mm	mm	mm	mm	M = Nut S = Screw	Poles / Cell [Nr.]	Connector Type	Approx. [± 5%] [L]	Approx. [± 5%] [Kg]	IR at 100% SoC [mΩ]
KL 10 P	10					M	2	M10	0,48	1,21	19,46
KL 17 P	17					M	2	M10	0,43	1,29	12,16
KL 21 P	21	46	85	237	262	M	2	M10	0,41	1,36	9,18
KL 26 P	26					M	2	M10	0,37	1,42	7,57
KL 30 P	30					M	2	M10	0,36	1,48	6,71
KL 35 P	35					M	2	M10	0,87	2,28	5,50
KL 40 P	40					M	2	M10	0,85	2,36	5,39
KL 45 P	45					M	2	M10	0,81	2,44	4,32
KL 50 P	50					M	2	M10	0,78	2,52	4,44
KL 55 P	55	85	85	237	262	M	2	M10	0,76	2,59	3,96
KL 60 P	60					M	2	M10	0,72	2,67	3,36
KL 65 P	65					M	2	M10	0,69	2,74	3,53
KL 70 P	70					M	2	M10	0,65	2,81	3,02
KL 75 P	75					M	2	M10	0,62	2,89	2,66
KL 80 P	80					S	2	M8	1,36	4,70	2,57
KL 85 P	85					S	2	M8	1,33	4,76	2,60
KL 95 P	95	53	134	364	392	S	2	M8	1,19	4,99	2,31
KL 100 P	100					S	2	M8	1,16	5,07	2,10
KL 110 P	110					S	2	M8	1,21	5,11	1,97
KL 115 P	115					S	2	M8	1,18	5,19	1,94
KL 120 P	120					M/S	2	M16/M8	1,67	6,16	1,79
KL 125 P	125					M/S	2	M16/M8	1,63	6,26	1,65
KL 135 P	135					M/S	2	M16/M8	1,71	6,34	1,63
KL 145 P	145	69	134	364	392	M/S	2	M16/M8	1,67	6,44	1,58
KL 150 P	150					M/S	2	M16/M8	1,49	6,67	1,50
KL 160 P	160					M/S	2	M16/M8	1,56	6,74	1,37
KL 170 P	170					M/S	2	M16/M8	1,52	6,85	1,21
KL 180 P	180					M/S	2	M16/M8	3,89	10,10	1,26
KL 190 P	190					M/S	2	M16/M8	3,60	10,2	1,02
KL 200 P	200					M/S	2	M16/M8	3,77	10,5	1,04
KL 210 P	210					M/S	2	M16/M8	3,49	10,5	1,04
KL 215 P	215					M/S	2	M16/M8	3,71	10,7	0,99
KL 225 P	225					M/S	2	M16/M8	3,43	10,7	0,85
KL 240 P	240					M/S	2	M16/M8	3,59	11,1	0,85
KL 250 P	250	108	164	364	392	M/S	2	M16/M8	3,53	11,2	0,84
KL 255 P	255					M/S	2	M16/M8	3,26	11,2	0,88
KL 265 P	265					M/S	2	M16/M8	3,18	11,5	0,80
KL 270 P	270					M/S	2	M16/M8	3,42	11,6	0,79
KL 290 P	290					M/S	2	M16/M8	3,34	11,8	0,77
KL 300 P	300					M/S	2	M16/M8	3,02	12,0	0,75
KL 305 P	305					M/S	2	M16/M8	3,24	12,2	0,65
KL 320 P	320					M/S	2	M16/M8	2,93	12,3	0,63
KL 340 P	340					M/S	2	M16/M8	3,06	12,7	0,63
KL 350 P	350					S	2	M10	5,09	15,8	0,63
KL 360 P	360	164	158	364	392	S	2	M10	5,03	16,0	0,57
KL 370 P	370					S	2	M10	5,33	16,4	0,59
KL 385 P	385					S	2	M10	4,92	16,3	0,59

\* All dimensions and weights stated are subject to usual manufacturing tolerances. The right is reserved to make any alterations without prior notice.

## KL... P Single Cell Range

### Technical Specifications

"KL Type Models"	IEC-60623 Capacity	"Cell Dimensions [Tolerance ±2 mm]"				Connection Type	Nr. Of Terminals	Type of Terminals	Electrolyte Volume	Filled Cell Weight	Internal Resistance
		l	w	h	h1						
In Plastic Containers	5h rate [C <sub>5</sub> ] [Ah]	mm	mm	mm	mm	M = Nut S = Screw	Poles / Cell [Nr.]	Connector Type	Approx. [± 5%] [L]	Approx. [± 5%] [Kg]	IR at 100% SoC [mΩ]
KL 390 P	390					S	2	M10	4,88	16,5	0,55
KL 400 P	400					S	2	M10	5,23	16,9	0,51
KL 415 P	415					S	2	M10	4,76	16,8	0,53
KL 420 P	420					S	2	M10	4,72	17,3	0,52
KL 430 P	430					S	2	M10	5,04	17,2	0,47
KL 440 P	440					S	2	M10	4,98	17,7	0,50
KL 445 P	445	164	158	364	392	S	2	M10	4,59	17,3	0,45
KL 455 P	455					S	2	M10	4,56	17,8	0,46
KL 465 P	465					S	2	M10	4,86	18,0	0,43
KL 470 P	470					S	2	M10	4,80	18,2	0,45
KL 480 P	480					S	2	M10	4,42	17,7	0,46
KL 500 P	500					S	2	M10	4,67	18,6	0,42
KL 515 P	515					S	2	M10	4,63	18,8	0,40
KL 540 P	540					S	2	M10	4,49	19,2	0,41
KL 550 P	550					S	4	M10	9,07	27,0	0,40
KL 575 P	575					S	4	M10	8,93	27,6	0,36
KL 595 P	595					S	4	M10	8,77	28,0	0,38
KL 610 P	610	176	246	382	408	S	4	M10	8,74	28,1	0,33
KL 635 P	635					S	4	M10	8,59	28,5	0,32
KL 655 P	655					S	4	M10	8,57	28,8	0,32
KL 680 P	680					S	4	M10	8,41	29,1	0,33
KL 720 P	720					S	4	M10	8,22	30,1	0,30
KL 750 P	750					S	6	M10	14,2	40,1	0,30
KL 770 P	770					S	6	M10	14,1	40,5	0,29
KL 800 P	800					S	6	M10	13,9	41,4	0,28
KL 815 P	815					S	6	M10	13,9	40,9	0,27
KL 865 P	865					S	6	M10	13,7	41,8	0,23
KL 890 P	890	176	368	382	418	S	6	M10	13,4	42,4	0,26
KL 915 P	915					S	6	M10	13,4	42,4	0,24
KL 950 P	950					S	6	M10	13,2	43,1	0,20
KL 980 P	980					S	6	M10	13,1	43,5	0,20
KL 1030 P	1030					S	6	M10	12,9	44,0	0,19
KL 1080 P	1080					S	6	M10	12,6	45,5	0,18
KL 1100 P	1100					S	8	M10	16,5	52,1	0,18
KL 1150 P	1150					S	8	M10	16,2	53,4	0,17
KL 1190 P	1190					S	8	M10	16,0	54,1	0,18
KL 1220 P	1220	176	448	382	418	S	8	M10	15,9	54,2	0,19
KL 1270 P	1270					S	8	M10	15,6	55,1	0,16
KL 1300 P	1300					S	8	M10	15,6	55,7	0,17
KL 1350 P	1350					S	8	M10	15,2	56,3	0,16
KL 1450 P	1450					S	8	M10	14,9	58,3	0,15
KL 1500 P	1500					S	10	M10	19,9	66,9	0,15
KL 1540 P	1540					S	10	M10	19,8	67,0	0,14
KL 1600 P	1600	176	558	382	418	S	10	M10	19,4	68,2	0,14
KL 1630 P	1630					S	10	M10	19,4	68,9	0,13
KL 1700 P	1700					S	10	M10	19,0	69,6	0,13
KL 1800 P	1800					S	10	M10	18,5	72,1	0,11

\* All dimensions and weights stated are subject to usual manufacturing tolerances. The right is reserved to make any alterations without prior notice.



# GAZ VENTED KM BATTERY RANGE

This GAZ<sup>®</sup> Vented range KM cell type has been optimally designed for mixed load applications where these cells are capable of delivering variable high and also low rate discharges with economical battery capacity sizing. The discharges can generally be infrequent and the recommended discharge time for the KM range is between 30 minutes till 3 hours.

The nominal C<sub>5</sub> capacity of KM range batteries is based on the available ampere hours (Ah) at a discharge rate of 5 hours to a final discharge voltage of 1.15 V per cell (as per DIN 40771) and 1.00 V per cell (as per IEC 60623) at 20 ± 5 °C.

## Nominal voltage per cell

1.20 V per cell

## Discharging conditions

The discharge performances as well as the nominal capacities C<sub>5</sub> given in this brochure are only valid for fully charged cells in accordance with IEC 60623 und EN 60623, clause number 7.3.2.

## Charging Recommendation - KM Range

### A. Constant Voltage (FCBC Chargers)

Recommendation for Stand-by Application

### Boost Mode

Boost Voltage: 1.55–1.70 V/cell

Boost Current Limit: 0.2 It A dc

**NOTE:** Higher Boost voltage will reduce the charge duration and increase efficiency of recharging but may increase electrolysis and water consumption.

### Float Mode

Float Voltage: 1.40–1.42 V/cell

Float Current: 1 to 2 mA/Ah cell capacity

Delay for switch from Boost to Float:

Boost Current ramped < 0.004 It A

### Single level Charging

1.46–1.49 V/cell

## B. Constant Current mode

### Charging for IEC Capacity Test

Constant Current: 0.2 It A dc for 8 h

Alternatively, 0.1 It A dc for 16 h


Voltage Limit: No Voltage Limit

Charging Temperature: 20 ± 5 °C

### Fast Charging at 25 °C

Boost charge: 0.3 It A for 2.5 h followed by 0.2 It A for 2.5 h

Trickle charge: 0.001–0.002 A/Ah



## KM... P Single Cell Range

### Technical Specifications

KM Type Models	IEC-60623 Capacity	DIN-40771 Capacity	Cell Dimensions [Tolerance ±2 mm]				Connection Type	Nr. Of Terminals	Type of Terminals	Electrolyte Volume	Filled Cell Weight	Internal Resistance
			l	w	h	h1						
In Plastic Containers	5h rate [C <sub>5</sub> till 1.0V EOD]	5h rate [C <sub>5</sub> till 1.15V EOD]	mm	mm	mm	mm	M = Nut S = Screw	Poles / Cell [Nr.]	Connector Type	Approx. [± 5%] [L]	Approx. [± 5%] [Kg]	IR at 100% SoC [mΩ]
KM 11 P	12	11	46	85	167	191	M	2	M 10	0,31	1,0	13,64
KM 18 P	19	18					M	2	M 10	0,44	1,5	8,37
KM 24 P	26	24	46	85	237	262	M	2	M 10	0,38	1,5	6,30
KM 30 P	33	30					M	2	M 10	0,31	1,6	5,05
KM 40 P	44	40					M	2	M 10	0,84	2,7	3,81
KM 48 P	52	48	85	85	237	262	M	2	M 10	0,74	2,8	3,23
KM 55 P	61	55					M	2	M 10	0,64	2,9	2,96
KM 65 P	71	65	53	134	364	392	S	2	M 8	1,30	4,7	2,55
KM 75 P	82	75					S	2	M 8	1,17	4,9	2,23
KM 90 P	99	90	69	134	364	392	S	2	M 8	1,74	6,0	1,88
KM 110 P	121	110					S	2	M 8	1,50	6,5	1,54
KM 125 P	137	125	70	164	364	392	S	2	M 8	2,20	7,4	1,42
KM 140 P	154	140					S	2	M 8	1,73	7,7	1,28
KM 160 P	176	160					S	2	M 8	3,54	10,7	1,12
KM 185 P	203	185					S	2	M 8	3,27	11,0	0,98
KM 205 P	225	205	108	164	364	392	S	2	M 8	2,98	11,3	0,90
KM 225 P	247	225					S	2	M 8	2,83	11,8	0,83
KM 250 P	275	250					S	2	M 8	2,68	12,1	0,76
KM 270 P	297	270					S	2	M 10	5,22	16,3	0,71
KM 300 P	330	300					S	2	M 10	4,98	16,0	0,65
KM 320 P	352	320					S	2	M 10	4,79	16,5	0,62
KM 340 P	374	340	164	158	364	392	S	2	M 10	4,60	17,0	0,59
KM 355 P	390	355					S	2	M 10	4,31	18,0	0,57
KM 380 P	418	380					S	2	M 10	4,12	18,6	0,54
KM 400 P	440	400					S	2	M 10	3,93	18,9	0,51
KM 420 P	460	420					S	4	M 10	7,19	25,4	0,49
KM 450 P	499	450					S	4	M 10	7,0	27,3	0,46
KM 470 P	520	470					S	4	M 10	7,0	28,5	0,44
KM 500 P	555	500	176	246	382	408	S	4	M 10	6,8	28,3	0,42
KM 520 P	575	520					S	4	M 10	6,8	29,1	0,41
KM 550 P	610	550					S	4	M 10	6,6	28,2	0,38
KM 570 P	630	570					S	4	M 10	6,6	30,4	0,38
KM 600 P	665	600					S	6	M 10	13,1	39,8	0,36
KM 630 P	700	630					S	6	M 10	13,1	40,3	0,35
KM 675 P	750	675	176	368	382	418	S	6	M 10	12,3	41,8	0,34
KM 705 P	785	705					S	6	M 10	12,3	42,9	0,33
KM 750 P	835	750					S	6	M 10	10,6	42,9	0,31
KM 850 P	945	850					S	8	M 10	15,3	48,8	0,28
KM 950 P	1060	950					S	8	M 10	14,2	53,2	0,25
KM 1000 P	1110	1000	176	448	382	418	S	8	M 10	12,7	56,0	0,24
KM 1050 P	1165	1050					S	8	M 10	12,7	58,8	0,23
KM 1150 P	1275	1150					S	10	M 10	19,4	63,4	0,21
KM 1250 P	1390	1250	176	558	382	418	S	10	M 10	17,3	68,9	0,20
KM 1390 P	1545	1390					S	10	M 10	17,7	77,0	0,18

\* All dimensions and weights stated are subject to usual manufacturing tolerances. The right is reserved to make any alterations without prior notice.

# GAZ VENTED KH BATTERY RANGE

This GAZ® Vented range KH cell type has been optimized for power demanding applications where these cells are capable to deliver high rate discharge current with economical battery capacity sizing. Typically for short-period inrush power applications. The discharges can generally be unpredictable and infrequent. The recommended discharge period for the KH range is typically between 1 second up to 45 minutes.

The nominal C<sub>5</sub> capacity (as per IEC 60623) of KH range batteries is based on the available ampere hours (Ah) at a discharge rate of 5 hours to a final discharge voltage of 1.00 V per cell at 20 ± 5 °C.

**Nominal voltage per cell**  
1.20 V per cell

### Discharging conditions

The discharge performances as well as the nominal capacities C<sub>5</sub> given in this brochure are only valid for fully charged cells in accordance with IEC 60623 und EN 60623, point 4.1.

### Charging Recommendations – KH Range

#### A. Constant Voltage (FCBC Chargers)

Recommendation for Stand-by Application

#### Boost Mode

Boost Voltage: 1.55–1.70 V/cell  
Boost Current Limit: 0.2 It A dc

**NOTE:** Higher Boost voltage will reduce the charge duration and increase efficiency of recharging but may increase electrolysis and water consumption.

#### Float Mode

Float Voltage: 1.40–1.42 V/cell  
Float Current: 1 to 2 mA/Ah cell capacity

Delay for switch from Boost to Float:  
Boost Current ramped < 0.004 It A

#### Single level Charging

1.44–1.48 V/cell

#### Engine Starting Applications

1.50–1.55 V/cell


### B. Constant Current mode

#### Charging for IEC Capacity Test

Constant Current: 0.2 It A dc for 8 h  
Alternatively, 0.1 It A dc for 16 h  
Voltage Limit: No Voltage Limit  
Charging Temperature: 20 ± 5 °C

#### Fast Charging at 25 °C

Boost charge: 0.3 It A for 2.5 h followed by 0.2 It A for 2.5 h  
Trickle charge: 0.001–0.002 A/Ah




## KH... P Single Cell Range

### Technical Specifications

"KL Type Models"	IEC-60623 Capacity	"Cell Dimensions [Tolerance ±2 mm]"				Connection Type	Nr. Of Terminals	Type of Terminals	Electrolyte Volume	Filled Cell Weight	Internal Resistance
In Plastic Containers	5h rate [C <sub>5</sub> ] [Ah]	l [mm]	w [mm]	h [mm]	h1 [mm]	M = Nut S = Screw	Poles / Cell [Nr.]	Connector Type	Approx. [± 5%] [L]	Approx. [± 5%] [Kg]	IR at 100% SoC [mΩ]
KH 10 P	10	46	85	237	262	M	2	M 10	0,7	1,6	10,35
KH 20 P	20					M	2	M 10	0,6	1,9	5,18
KH 30 P	30					S	2	M 8	1,9	4,0	3,49
KH 40 P	40	53	134	330	360	S	2	M 8	1,9	4,2	2,67
KH 50 P	50					S	2	M 8	1,8	4,5	2,21
KH 65 P	65	69	134	330	360	S	2	M 8	2,4	5,8	1,72
KH 80 P	80					S	2	M 8	2,3	6,1	1,48
KH 100 P	100	104	134	330	360	S	2	M 8	3,6	8,8	1,22
KH 125 P	125					S	2	M 8	3,7	9,7	1,00
KH 150 P	150	108	164	330	360	S	4	M 8	4,4	11,9	0,85
KH 185 P	185					S	4	M 8	6,1	15,2	0,70
KH 200 P	200	164	158	330	360	S	4	M 8	6,2	15,6	0,68
KH 235 P	235					S	4	M 8	6,4	16,6	0,63
KH 250 P	250					S	4	M 8	6,4	17,0	0,61
KH 280 P	280					S	4	M 10	9,5	23,7	0,56
KH 300 P	300	176	246	330	360	S	4	M 10	9,5	24,2	0,53
KH 320 P	320					S	4	M 10	9,2	24,6	0,51
KH 360 P	360					S	6	M 10	15,0	33,9	0,45
KH 390 P	390					S	6	M 10	14,9	34,7	0,42
KH 420 P	420	176	368	330	360	S	6	M 10	14,7	35,4	0,40
KH 450 P	450					S	6	M 10	14,6	36,3	0,38
KH 480 P	480					S	6	M 10	14,4	37,0	0,36
KH 520 P	520					S	8	M 10	18,5	44,7	0,34
KH 560 P	560	176	448	330	360	S	8	M 10	18,4	45,9	0,33
KH 600 P	600					S	8	M 10	18,3	47,0	0,31
KH 640 P	640					S	8	M 10	18,1	48,1	0,30
KH 700 P	700					S	10	M 10	23,0	57,2	0,28
KH 750 P	750	176	558	330	360	S	10	M 10	22,8	58,6	0,26
KH 800 P	800					S	10	M 10	22,6	60,0	0,25

\* All dimensions and weights stated are subject to usual manufacturing tolerances. The right is reserved to make any alterations without prior notice.



## SUPERBLY RELIABLE AND COST-EFFECTIVE

Nickel-cadmium cells are immune to thermal runaway and do not suffer sudden death. The unique electrochemistry of GAZ® Ni-Cd batteries also enables them to withstand any depth of discharge. At the same time, their low self-discharge rate makes them ideal for applications where the battery may not be used for extended periods.

Thanks to their exceptional ruggedness and minimal maintenance requirements, Ni-Cd batteries are the first choice for even the most challenging industrial, commercial, governmental and military applications.

### Unique Features of GAZ® Nickel cadmium cells

Setting some benchmark for industrial Ni-Cd batteries

- ✓ Single cell design for all rated capacities are housed in unique mono-block plastic containers that has seamless, non-welded surface on all side walls and bottom of cell container.
- ✓ All GAZ® cell containers are produced as one unit from a single injection moulding. This ensures that liquid electrolyte inside the cell can never be stagnant in contact with any plastic welded area.
- ✓ This ability prevent any chance of leakage of electrolyte and corresponding fire hazard in entire service life of GAZ® cells and minimizing handling and environmental hazards.
- ✓ More available capacity steps – More flexibility, in selection of sized battery for applications.
- ✓ The extended range of GAZ® Ni-Cd Pocket plate cells reaches a new height of standard in the industry. Single 1.2V GAZ® Vented KL..P cell can now have 1800 Ah capacity,
- ✓ Harmonized active mass distribution ratio among electrodes ensures the standardized Quality in production, minimizing Quality deviations.
- ✓ Increased rechargeability, Faster recharge ensures maximum availability and system reliability.

### Reliable performance in extreme temperatures

Generally operating in temperatures from -20 °C to +50 °C, GAZ® Ni-Cd batteries can tolerate extremes up to +70 °C for short periods of time and can also operate up to -50 °C with special GAZ® electrolytes.

### Easy storage and installation

GAZ® Ni-Cd batteries are quick and easy to install as original equipment and may be stored for a longer period in unfilled and discharged state under recommended conditions.

On installation a simple bolted connector enables the cells to be rapidly connected and commissioned in suitable battery racks or cabinets.

### Low Total Cost of Ownership

GAZ® Ni-Cd batteries are designed to operate hassle-free for over 20+ years of designed lifetime with minimal comparable maintenance efforts, as per Annex – G of IEEE 1184-2006. Their superb quality further contributes to the particularly low TCO of GAZ® Ni-Cd battery systems against other conventional electrochemistry for a typical service life of 20+ years.



## DESIGN YOUR BATTERY SOLUTION

Visit the GAZ® website for our easy-to-use Ni-Cd battery Calculator, a tool that allows you to quickly estimate or determine which battery configuration, type and size is best suited for your application. It will give you an idea of the battery storage system you need even before you inquire with the GAZ® sales department. The on-line battery calculator estimate the sizing in accordance to IEEE-1115, Recommended Practice for Sizing Nickel-Cadmium Batteries for Stationary Applications.

### NI-CD CALCULATOR

1

#### Load Profile

Current calculator			
1. Period	Time	00:00:00	hh:mm:ss
	Current	0	amper
+	Time	00:00:00	hh:mm:ss
	Current	00	amper

Through a guided User-Interface, fill in the basic parameters of the required or expected load the batteries will be handling for a specific application.

The load input can be either with load in terms of current [A] or Apparent Power [KVA] or Real Power [KW] for load duration in hh:mm:ss. For instances of multiple loads in an application profile, select '+' to add these loads in their appropriate sequence.

2

#### Cell Quantity

Nominal Battery Voltage

Select or specify the DC system voltage for the application and the number of cells your battery set should contain with regards to their nominal voltage and end-of-discharge or DC system cut-off voltage.

3

#### Design Data

Ambient temperature °C / °F

Aging factor

Design margin factor

Input the operating environment for the battery in the application. Other key requirements can be factored and filtered into the evaluation as well.

Once the battery is calculated, you are one click away to generate and download a complete report in PDF format that consist of battery sizing as per IEEE-1115 and ventilation requirements as per IEC 62485-2 or EN 50272-2.

In case you require an battery sizing assistance or want to check possibility of further optimization of the sizing to increase the competitiveness, contact our global sales team or partners to create or optimize your sizing needs with our professional complex battery software.

The output will be a recommendation that is not only technologically, but also economically the most favorable.





## OUR COMMITMENT TO THE ENVIRONMENT

At GAZ®, as one of the leading manufacturer of Ni-Cd batteries for over 100 years, we pay rightful attention to the environmental footprint of our batteries. Proper recycling prevents pollution but also enables the recovery of materials that can be reused. Starting from the optimized design, GAZ® Ni-Cd batteries are composed of harmonized production elements that make their recycling more efficient and cost-effective without compromising the product performance and design lifetime.

The recycling efficiency reaches nearly 80% of the cell weight, which is higher than the prescribed recycling efficiency of 75% by regulations applicable to Ni-Cd batteries.

All GAZ® batteries are disposed of with certified long-term partners in compliance to regional regulations. GAZ® also provides a recycling testimonial with unique recycling case number for complete traceability.

### Regulatory compliance

- ✓ **EU Declaration of Conformity** – GAZ® confirms and bear the responsibility of self-declaration of conformity of produced Ni-Cd cells according to recently adopted EU Battery Regulation.
- ✓ **RoHS** – Even though accumulators are not within the scope of EU's Restriction of Hazardous Substances (RoHS) regulation, GAZ® voluntarily declares that the substances restricted by RoHS are not present in our batteries except for their electrochemical core.
- ✓ **REACH** – About EU's Registration, Evaluation, Authorisation and Restriction of Chemicals (REACH), GAZ® voluntarily declares that our Ni-Cd accumulators contain more than 0.1% w/w of Cadmium (Cd) substances depending on delivery status.



/ Vented Single Cell Ni-Cd Battery Range

## CONTACTS



### GAZ Energy a.s.

Tovární 319  
735 81 Bohumín  
Czech Republic

E: sales@gaz-gmbh.com

[www.gaz-gmbh.com](http://www.gaz-gmbh.com)

### GAZ Geräte – und Akkumulatorenwerk Zwickau GmbH

Reichenbacher Str. 62–68  
080 56 Zwickau  
Germany

P: +49 375 86 0  
E: sales@gaz-gmbh.com

[www.gaz-gmbh.com](http://www.gaz-gmbh.com)

### GAZ Middle East Industry Company

Gushat Tower, Floor-3  
Prince Hammoud Street,  
Aqrabiyah  
P.O.BOX – 3631  
319 52 Al Khobar  
Kingdom of Saudi Arabia

E: sales@gaz-gmbh.com

[www.gaz-gmbh.com](http://www.gaz-gmbh.com)

### GAZ Energy, LLC.

4404-A West 12th Street  
Houston, TX, 77055  
United States of America

P: +1 (346) 460 3482  
E: sales@gaz-gmbh.com

[www.gaz-gmbh.com](http://www.gaz-gmbh.com)





GAZ Geräte - und Akkumulatorenwerk Zwickau GmbH  
Reichenbacher Str. 62-68, 08056 Zwickau, Germany  
T: +49 375 86 0, F: +49 375 86 440, E: sales@gaz-gmbh.com

[www.gaz-gmbh.com](http://www.gaz-gmbh.com)